



NATIONAL ACRYL EMULSION II

PRODUCT DESCRIPTION	National Acryl Emulsion II is an Acrylic copolymer based, washable interior/exterior emulsion paint with a smooth flat decorative finish. It offers excellent adhesion and recoatability. National Acryl Emulsion II is with better hiding power and exceptional light and weather resistances. Basically, it is for masonry application purpose, with good alkali resistance. It contains anti fungal and anti bacterial additives.
----------------------------	--

RECOMMENDED USES	National Acryl Emulsion II is recommended for the masonry applications like concrete, plaster, stucco filler, gypsum board, asbestos, blocks etc. It is also used for sealing the surfaces of stucco filler and gypsum board for the subsequent coatings like National Eggshell Emulsions. It is recommended for the interior/exterior applications of flats, buildings, offices, boundary wall etc. It can be applied over wooden surfaces also.
-------------------------	---

TECHNICAL DATA

COLOUR, DRY FILM	As per the National Shade Card
FINISH, DRY FILM	Smooth / Matt
VOLUME SOLIDS (ASTM D2697)	44 ± 2 %
SPECIFIC GRAVITY	1.50 ± 0.05
THEORETICAL SPREADING	11 – 9 M ² /LTR
RECOMMENDED DFT (DRY FILM)	40 – 50 Microns / Coat
RECOMMENDED WFT (WET FILM)	90 – 115 Microns / Coat
FLASH POINT	Water Base

DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.)	
TOUCH DRY	1 hour
DRY TO RECOAT	2 – 4 hours
FULL DRY	24 hours



ADVANTAGES

NATIONAL ACRYL EMULSION II	Washable interior/exterior paint, excellent recoatability and adhesion, exceptional light and weather resistances, suitable for all masonry surfaces, good alkali resistance, smooth and flat decorative economical finish.
-----------------------------------	---

APPLICATION INSTRUCTION

SURFACE PREPARATION	Before application, the surface should be sound, clean and free from oil, grease, loose particles, dust, etc. Application can be done by the recommended application methods.
----------------------------	---

APPLICATION DATA

APPLICATION METHOD	Roller, Brush, Spray etc.
CLEANING/THINNING	Water
THINNER (VOLUME)	5 – 10 % depends on method of application
CONV. SPRAY REQUIREMENTS	Possible
AIRLESS SPRAY REQUIREMENTS	Pressure: 2000 – 2500 psi
NOZZLE SIZE	0.018” - 0.021”
MIXING RATIO (BY VOLUME)	NA
POT LIFE @ 30°c (100 ml)	NA

SYSTEM

RECOMMENDED SYSTEM To be applied on prepared surface.	National PVA Primer Sealer for Masonry	:	1 coat
	(OR)		
	National PVA Primer White for Masonry	:	1 coat
	(OR)		
	National Acrylic Primer (W.B.)	:	1 coat
	National Stucco Filler (for Interior only)	:	2 coats
	National Acryl Emulsion II	:	2 coats

NATIONAL/INTERNATIONAL TEST CERTIFICATES

Sr. No.	Test Description	Test Reference	Compliance
1	Fungal Resistance	ASTM D 3273	



ADDITIONAL DATA

SHELF LIFE @ 30°C	18 months, in original sealed container, with proper storage conditions.
--------------------------	--

HEALTH & SAFETY

SAFETY PRECAUTIONS	Generally, most of the water base paints are quite safe to handle with due precautions. As a general rule, avoid skin and eye contact by wearing overalls, gloves, goggles, and mask etc. spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapours and paint mist by wearing suitable mask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area. Local safety regulations to be followed.
-------------------------------	--

STORAGE & HANDLING

STORAGE	Store the paint in proper storage conditions as per the local regulations. Keep the paint container in sealed condition under shed, away from direct sunlight and extreme temperatures. Do not keep paint material near to any ignition sources. Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination. Handle with care. Stir well before use.
----------------	---

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details refer specifier and safety data.

This data sheet supersedes all previous issued.
Issued: 0718