

NATIONAL AUTO GLOSS PAINT

DESCRIPTION	A special Alkyd base quick drying and glossy finish which is hard and weather resistant, its high gloss does not require any polishing.
RECOMMENDED USE	Suitable for Interior / Exterior and all wooden, masonry and metallic surfaces especially heavy duty equipment.

TECHNICAL DATA

Colors	As per shade card.
Finish	Glossy.
Solid by Weight %	60 ± 5%
Viscosity (25°C)	7.5 - 8.5 Poise.
Specific Gravity	1.07 ± 0.1 (for White and Pastel shades).
Coverage Rate (2 coats 10% dilution)	4 - 8 m ² /Lit. (depending on the color used).
Film Thickness	(Dry Film) 30 microns ≈ 1.2 mils. (Wet Film) 60 microns ≈ 2.4 mils.
Flash point	32°C

DRYING TIME

Touch dry	1 hr.
Hard dry	3 hrs.

SURFACE PREPARATION

Surface should be cleaned and dry thoroughly and should be applied over National N.C. Putty or National N.C Primer .
--

APPLICATION DATA

Application Methods	Spray
Thinning / Cleaning of Tools	National Special Thinner.
Mixing Ratio	7.5% hardener may be added to improve performance.
Guiding Data for Airless Spray	Nozzle Tip: 0.015" - 0.02". Nozzle Pressure: 2200 P.S.I.

MISCELLANEOUS DATA

STORAGE	The product must be stored according to National Regulations. The product should be kept in a cool and well ventilated place, protected from heat and direct sunlight at temp 5-35°C. Containers must be kept tightly closed.
HANDLING	Handle with care, mix well before use.
SHELF LIFE	36 months, in original sealed container, with proper storage conditions.
SAFETY / HEALTH	<ul style="list-style-type: none"> - Ensure good ventilation during application and drying. - Avoid contact with skin and eyes. While painting it is advisable to wear eye protector. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. To remove splashes from skin; use soap and water or a recognized skin cleaner. - Keep out of reach of children.
TDS ISSUE NO. & DATE	(3) - June 2017

NOTE: We warranty the quality of our product and this data sheet represents test results and practical experience obtained under controlled conditions. We reserve the right to change data without prior notice.