

NATIONAL GRAVEL GUARD (GOMA)

DESCRIPTION

A special resin blend base undercoat which gives a tough textured undercoat to the refinishing that gives extra protection against stone and gravel chipping. Has good color retention, high resistance to severe weather conditions, good durability and flexibility.

RECOMMENDED USE

For refinishing plastisol area on cars as replacement coating.

TECHNICAL DATA

Color	White, Black.
Finish	Matt textured.
Viscosity (25°C)	8 - 12 Poise.
Specific Gravity	1.45 ± 0.07
Solid by Weight %	70 ± 5%
Theoretical Spreading Rate	5 - 12 m ² /Lit.
Film Thickness	(Dry Film) 70 microns.
Impact resistance (25 cm)	pass
Scratch resistance	pass
Bending test (15 mm)	pass
Water resistance (24 hrs) spot test	pass

DRYING TIME

Touch dry	5 - 10 min.
Hard dry	8 hrs.

SURFACE PREPARATION

Surface must be clean, dry and free from oil grease, dirt etc.

APPLICATION DATA

Application Methods	Special Spray Gun.
Thinning / Cleaning of Tools	Ready for use, could be diluted with Synthetic Thinner
Guiding Data for Airless Spray	Nozzle Tip: 0.015" - 0.20" Nozzle Pressure: 2200 P.S.I.

MISCELLANEOUS DATA

STORAGE	The product must be stored according to National Regulations. The product should be kept in a cool and well ventilated place, protected from heat and direct sunlight at temp 5-35°C. Containers must be kept tightly closed.
HANDLING	Handle with care, mix well before use.
SHELF LIFE	18 months, in original sealed container, with proper storage conditions.
SAFETY / HEALTH	<ul style="list-style-type: none"> - Ensure good ventilation during application and drying. - Avoid contact with skin and eyes. While painting it is advisable to wear eye protector. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. To remove splashes from skin; use soap and water or a recognized skin cleaner. - Keep out of reach of children.
TDS ISSUE NO. & DATE	(3) - June 2017

NOTE: We warranty the quality of our product and this data sheet represents test results and practical experience obtained under controlled conditions. We reserve the right to change data without prior notice.