

NATIONAL FAST CUT POLISH

DESCRIPTION	A special water base formulation based on resins and coarse silica which cleans the surface, removes imperfections in the finish and polishes it to give a very smooth surface.
RECOMMENDED USE	Use before National Soft Polish for automotive finishes (National N.C. and Acrylic Polyurethane).

TECHNICAL DATA

Colors	Orange
Viscosity (25°C)	Paste like
Specific Gravity	1.39 ± 0.05
Solid By Weight% (110°C)	54 ± 5%
PH	9.5 ± 1
Silica Contents (<=75µ)	53 ± 4 %
Oil Contents (P.B<80°C)	17 ± 4%

SURFACE PREPARATION

Should be dry, clean and free from all loose particles.

APPLICATION DATA

Thinning / Cleaning of Tools	By cotton or special tool. Put polish on the surface and apply several times by equal pressure on the surface with smooth cloth or cotton, then this use National Soft Polish to maximise the gloss.
Cleaning of Tools	Water.

CONDITIONS DURING APPLICATION

The temperature of the substrate should be minimum 10°C above the dew point and relative humidity measured in the substrate vicinity.

NOTE: Polishing should be carried out after complete drying of paint and according to paint system.

MISCELLANEOUS DATA

STORAGE	The product must be stored according to National Regulations. The product should be kept in a cool and well ventilated place, protected from heat and direct sunlight at temp 5-35°C. Containers must be kept tightly closed.
HANDLING	Handle with care, mix well before use.
SHELF LIFE	24 months, in original sealed container, with proper storage conditions.
SAFETY / HEALTH	<ul style="list-style-type: none"> - Ensure good ventilation during application and drying. - Avoid contact with skin and eyes. While painting it is advisable to wear eye protector. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. To remove splashes from skin; use soap and water or a recognized skin cleaner. - Keep out of reach of children.
TDS ISSUE NO. & DATE	(3) - June 2017

NOTE: We warranty the quality of our product and this data sheet represents test results and practical experience obtained under controlled conditions. We reserve the right to change data without prior notice.