



**TRANSOCEAN**

# Product Data Sheet

## Transpoxy ARC 2.22

### Product description.

A polyamine cured epoxy coating reinforced with a high content of extremely durable pigments. It combines an excellent abrasion resistance with premium anticorrosive properties and is compatible with properly applied cathodic protection. This makes Transpoxy ARC (Abrasion Resistance Coating) exceptionally suitable for areas where abrasion can be expected such as the outside hull and decks and holds.

### Physical properties.

Colour/Texture	Redbrown, Grey /Semi-gloss
Volume Solids	70%
Specific gravity	1.5 gr/ml
Flashpoint	>25°C

	Dry film thickness per coat (µ)	Wet film thickness per coat (µ)	Theoretical spreading rate (m <sup>2</sup> /l)
Range	80 – 200	115 – 285	8.8 – 3.5
Recommended	150	215	4.7

### Application data.

Mixing ratio By volume, base to hardener: 80 to 20.

Potlife 10°C: 3 hours, 20°C: 2 hours.

Guiding data Airless spray Pressure at nozzle: 150 -250 bar. Nozzle size: 0.38 - 0.66 mm.  
Spray angle: 40 - 80 degrees.  
Volume of thinner: 0 - 3%.

Brush/Roller Suitable for touch-up work only.

Thinner/Cleaner Transocean Epoxy Thinner 6.03.

Conditions Humidity: below 85% RH.  
Temperature of the paint before application: min: 10°C, max: 30°C.  
Substrate temperature: min: 10°C, max: 35°C.  
The temperature of the substrate should be at least 3°C above the dew point of the air. Air temperatures and relative humidity must be measured in the vicinity of the substrate.

### Drying and recoating times.

Substrate temperature	Touch dry	Dry to handle	Full cure	Dry to recoat	
				Minimum	Maximum (1)
10 °C	12 hours	24 hours	10 days	12 hours	5 days
23 °C	8 hours	12 hours	7 days	8 hours	4 days
30 °C	6 hours	8 hours	5 days	6 hours	2 days

(1) The surface should be dry and free from contaminants prior to overcoating. When the maximum recoating time is exceeded it may be necessary to roughen the surface to ensure intercoat adhesion. When in doubt, consult your nearest Transocean office.

## Surface preparation.

Steel	Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: min. Sa2,5 – ISO 8501:1. Apply Transpoxy ARC 2.22 immediately after the steel has been blasted and the quality of preparation has been approved. Transpoxy ARC 2.22 may also be applied on Transpoxy primers such as Transozinc Epoxy Primer ST 1.50. Ensure that primed surfaces are dry and free from salts and other contaminants prior to overcoating.
Repair	Corroded areas should be power tool cleaned to ISO-St3 or blast cleaned to ISO-Sa2 or better. Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

## Recommended paint system.

A typical system for immersion conditions is shown below.

Transozinc Epoxy Primer ST 1.50	1 x 50 $\mu$ dft.
Transpoxy ARC 2.22	2 x 150 $\mu$ dft.
Transvinypox 2.06	1 x 80 $\mu$ dft.

Subsequent coating with an appropriate Transocean Antifouling system.

## Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spillage on the skin should immediately be removed by thorough washing with lukewarm water and soap or a suitable industrial cleaner. Eyes should be flushed with fresh water and medical attention sought immediately. Spraying should be carried out under well-ventilated conditions. Avoid inhalation of solvent vapours and paint mist by wearing an air mask.

This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

## Disclaimer

*The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product.*

*Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product.*

*We reserve the right to change the product without notice.*

Date of issue: May 03.